

Diotrol Imprägnierung B.P.IV

Natural Oil Impregnation B.P.IV

#75100BPIV

Description	Diotrol Natural Oil Impregnation B.P.IV is a colorless, solvent-based wood impregnation. It's a long-term wood protection against fungi, termites and insects. Diotrol Natural Oil Impregnation B.P.IV is used for the chemical treatment of components made of softwood and hardwood. A glaze or top coat is required for weather protection.
	Complies with DIN / EN 68800 T3, with active ingredients against insect infestation. Do not use in living areas or in stables, also avoid contact with animal and food.
	Official approval CH-2014- 0009
Application area	Particularly sensitive areas such as: windows, shutters, garage doors, wooden structures and much more.
	Do not use in living areas or stables.
Binder & reactive agents	Combination of different natural oils of regenerating raw materials
Active agents / Biocide	Propiconazole, 0.6%, IPBC 0.3%, permethrin 0.1%
Solids	8 %
Spec. Gravity	0.830 kg/l
Degree of Gloss	Matt. The level of gloss may vary depending on the absorbency of the substrate and the application quantity.
Tints	Colorless
Packaging	1L, 5L, 25L, 200L
Storage	12 months in appropriate, cool place in closed original packaging. Store in a cool and dry place.
Condition of substrate	 General information on wood The wood must be clean, free of grease, resin and wax and may not contain more than 15% moisture.
	Resinous wood must be washed with nitro thinner.



 Planed wood must be sanded to ensure good anchorage of the coating. Weathered and greyed wood must be treated with #82500 Diotrol Degrayer. If the wood is severely cracked, it is considered to be "old wood" and is not suitable. Cracked parts must be replaced by new wood. New, only planed wood, which has been exposed to the weather for a long time, must be sanded or brushed with a hard brush and must be cleaned afterwards. Avoid using metal brushes, there is a risk of rusting due to the sanding dust. Edges must be rounded to a radius of 2.5mm. General information on old coatings The surface must be checked for suitability and load-bearing capacity for subsequent coatings. Non-bearing, poorly adhering old coats must be completely removed down to the sound wood substance. Do wash a firmly adhering, intact old coating with #82510 Diotrol Allclean and slightly abrade the surface. Old acrylic coatings must be completely removed. Old oil-based coatings must also be completely removed due to the risk of blistering. n order to assess the product practical, we recommend to create a sample beforehand. Brush, roller, sprayer (protective clothing recommended), dipping/flooding possible n case of a spray application, we recommend to level / smooth the surface with a brush. Do not apply at outside temperatures below 10°C or above 30°C or at extreme humidity of more han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation. 00 – 120 g/m² per coat on planed, sanded spruce wood May depend on the nature and absorbency of the substrate.
severely cracked, it is considered to be "old wood" and is not suitable. Cracked parts must be replaced by new wood. New, only planed wood, which has been exposed to the weather for a long time, must be sanded or brushed with a hard brush and must be cleaned afterwards. Avoid using metal brushes, there is a risk of rusting due to the sanding dust. Edges must be rounded to a radius of 2.5mm. General information on old coatings The surface must be checked for suitability and load-bearing capacity for subsequent coatings. Non-bearing, poorly adhering old coats must be completely removed down to the sound wood substance. Do wash a firmly adhering, intact old coating with #82510 Diotrol Allclean and slightly abrade the surface. Old acrylic coatings must be completely removed. Old oil-based coatings must also be completely removed due to the risk of blistering. In order to assess the product practical, we recommend to create a sample beforehand.
sanded or brushed with a hard brush and must be cleaned afterwards. Avoid using metal brushes, there is a risk of rusting due to the sanding dust. Edges must be rounded to a radius of 2.5mm. General information on old coatings The surface must be checked for suitability and load-bearing capacity for subsequent coatings. Non-bearing, poorly adhering old coats must be completely removed down to the sound wood substance. Do wash a firmly adhering, intact old coating with #82510 Diotrol Allclean and slightly abrade the surface. Old acrylic coatings must be completely removed. Old oil-based coatings must also be completely removed due to the risk of blistering. In order to assess the product practical, we recommend to create a sample beforehand. Brush, roller, sprayer (protective clothing recommended), dipping/flooding possible In case of a spray application, we recommend to level / smooth the surface with a brush. Do not apply at outside temperatures below 10°C or above 30°C or at extreme humidity of more han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation. $00 - 120 \text{ g/m}^2 \text{ per coat on planed, sanded spruce wood}$
 General information on old coatings The surface must be checked for suitability and load-bearing capacity for subsequent coatings. Non-bearing, poorly adhering old coats must be completely removed down to the sound wood substance. Do wash a firmly adhering, intact old coating with #82510 Diotrol Allclean and slightly abrade the surface. Old acrylic coatings must be completely removed. Old oil-based coatings must also be completely removed due to the risk of blistering. an order to assess the product practical, we recommend to create a sample beforehand. Brush, roller, sprayer (protective clothing recommended), dipping/flooding possible in case of a spray application, we recommend to level / smooth the surface with a brush. Do not apply at outside temperatures below 10°C or above 30°C or at extreme humidity of more han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation. 00 – 120 g/m² per coat on planed, sanded spruce wood
The surface must be checked for suitability and load-bearing capacity for subsequent coatings. Non-bearing, poorly adhering old coats must be completely removed down to the sound wood substance. Do wash a firmly adhering, intact old coating with #82510 Diotrol Allclean and slightly abrade the surface. Old acrylic coatings must be completely removed. Old oil-based coatings must also be completely removed due to the risk of blistering. In order to assess the product practical, we recommend to create a sample beforehand. Brush, roller, sprayer (protective clothing recommended), dipping/flooding possible in case of a spray application, we recommend to level / smooth the surface with a brush. Do not apply at outside temperatures below 10°C or above 30°C or at extreme humidity of more han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation.
The surface must be checked for suitability and load-bearing capacity for subsequent coatings. Non-bearing, poorly adhering old coats must be completely removed down to the sound wood substance. Do wash a firmly adhering, intact old coating with #82510 Diotrol Allclean and slightly abrade the surface. Old acrylic coatings must be completely removed. Old oil-based coatings must also be completely removed due to the risk of blistering. In order to assess the product practical, we recommend to create a sample beforehand. Brush, roller, sprayer (protective clothing recommended), dipping/flooding possible in case of a spray application, we recommend to level / smooth the surface with a brush. Do not apply at outside temperatures below 10°C or above 30°C or at extreme humidity of more han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation.
completely removed due to the risk of blistering. In order to assess the product practical, we recommend to create a sample beforehand. Brush, roller, sprayer (protective clothing recommended), dipping/flooding possible In case of a spray application, we recommend to level / smooth the surface with a brush. Do not apply at outside temperatures below 10°C or above 30°C or at extreme humidity of more han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation. 00 – 120 g/m ² per coat on planed, sanded spruce wood
Brush, roller, sprayer (protective clothing recommended), dipping/flooding possible In case of a spray application, we recommend to level / smooth the surface with a brush. Do not apply at outside temperatures below 10°C or above 30°C or at extreme humidity of more han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation. 00 – 120 g/m ² per coat on planed, sanded spruce wood
n case of a spray application, we recommend to level / smooth the surface with a brush. Do not apply at outside temperatures below 10°C or above 30°C or at extreme humidity of more han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation. 00 – 120 g/m ² per coat on planed, sanded spruce wood
Do not apply at outside temperatures below 10°C or above 30°C or at extreme humidity of more han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation. 00 – 120 g/m ² per coat on planed, sanded spruce wood
han 70%. Avoid direct sunlight. When applying indoors, ensure good ventilation. 00 – 120 g/m² per coat on planed, sanded spruce wood
00 – 120 g/m ² per coat on planed, sanded spruce wood
Nay depend on the nature and absorbency of the substrate.
Ready for use.
Apply 1x Diotrol Impregnation B.P.IV on all sides of the wood, if possible before fitting. Saturate end-grain wood well, several layers may be necessary, wet in wet application.
A glaze or top coat is required for weather protection.
n case of doubt, please contact the technical service.
Dust dry after 1 – 2 hours
Over paintable:
 After 12 hours with Diotrol Natural Oil Glaze.
 After 24 hours with an oil-based paint or solvent based varnish.
•



	Depending on the temperature, the application quantity, the air humidity and the substrate's absorbency.
Cleaning of tools	Immediately after use with turpentine substitute or universal thinner. Dissolve dry paint residues with nitro thinner or brush cleaner.
Important remarks	 Saturated rags can ignite by themselves. Spread and let them dry in the open air, or store them in an airtight metal can.
	Keep away from sources of ignition. Avoid sources of fire during work.
	Keep away from food for humans and animals.
Safety advice	Please read safety data sheet.
Remarks	This information is due to the current, technical know-how and is meant as recommendation and advice. Concerning all mentioned paint coat structures, we do not maintain completeness. Insufficient wood quality, lack of constructive wood-protection, drying cracks in solid wood and otherwise identified faults have to be admonished by the customer before painting or glazing. Because of the diversification and different kinds of substrates and practice, the user has to test our products mainly for his own purpose and has to use and apply them properly. For this, he is fully responsible. Verbal advice must be fixed obligatory by a signed document. If a new issue will be current, this edition will be no more available.

October 2018, mt/sky

info@diotrol.com www.diotrol.com

DIOTROL AG | SCHWEIZ Bodenackerstrasse 64 | CH-4657 Dullikon | 7+41 62 285 30 70 *MwSt.-Nr.* CHE-107-159.180 MWST *IBAN* CH51 0900 0000 4047 1116 4 | *BIC* POFICHBEXXX